

## PETRA BUILD CARE PRODUCTS

Reg. Office : 16, Doctor House, Kalanala, Bhavnagar - 364 001. Phone / Fax : + 91 - 278 - 2425804, Cell: + 91 - 9825836406

# Petra FILLIT 100 W: Technical Data Sheet

## Petra FILLIT 100 W : Chemical composition (%):

SiO <sub>2</sub>	> 55	CaO	> 2
Al <sub>2</sub> O <sub>3</sub>	> 31	K <sub>2</sub> O	> 1
Fe <sub>2</sub> O <sub>3</sub>	< 3	loss	< 1
MgO	< 1		

## Petra FILLIT 100 W : Physical properties

Particle Size (um) : 5-100 microns  
Particle Density (g/cm<sup>3</sup>) : 0.6-0.7 g/cc  
Bulk Density (g/cm<sup>3</sup>) : 0.26-0.45 g/cc  
Moisture : <0.5%  
Sinkers : <3%  
Hardness Mohs Scale : 5-7  
Loss on Ignition : 2% maximum  
Thermal Conductivity : 0.11 W/mK  
Reactivity : Inert/very low reactivity  
Crush Strength : 105-210 kg/cm<sup>2</sup> (1500 - 3000 psi)  
Oil Absorption : 16-18g oil/100g  
Flammability : Not combustible  
Melting point : 1500oC approx.  
Solubility Negligible in water

Note: Above all figures are approximate & may change as per raw material procurement. This figures do not show 100% accuracy.